




Imaging

Images do not accurately portray size or color.

Accu-Vu™ Imaging:



Comments:

General Report Comments:

Document No: 1105913 Validation Date: 13 January 2020

Identification

Mineral Type: Natural Beryl Color Description: Green

Variety: Emerald Shape: Rectangular

Carat Weight: 5.48 cts Cutting Style: Emerald Cut

Measurements: 12.78 x 9.77 x 6.63 mm

Comments:

Identification

American Gemological Laboratories™
America's first and most highly respected origin lab.

Founded in 1977,

AGL is an internationally recognized gemstone testing facility, specializing in comprehensive colored stone analyses.

AGL has the distinction of being the first laboratory in the United States to issue Country-of-Origin reports. Our company and its principals have a long tradition of research into the detection of and reporting on gem identification-and-classification, gemstone treatments and provenance determinations.

Our staff is composed of experts in the field of gemstone testing and reporting. Our findings reflect the latest knowledge and analytical techniques to ensure the highest standards are applied on every stone we test.

AGL's testing and reporting methodology provide you with unsurpassed quality and reliability. We are committed to providing the highest level of service and reporting that our clients and the industry have come to expect from the AGL.

Origin

Provenance: Afghanistan

Comments: Based on available gemological information, it is the opinion of the Laboratory that the origin of this material would be classified as Afghanistan.



Origin

Enhancement

Standard: Clarity Additional: None

Degree: Minor

Type: Modern

Stability Index: Very Good to Good

Comments: Emeralds are commonly clarity enhanced to reduce the visibility of fissures. Today, modern types of materials used to clarity enhance gemstones include various polymer-type resins, singly or in combination with other types of fillers.

Enhancement

| | | | | | | | | | |
|-----------|-----------|------|------|------|---|---|---|---|----|
| 1 | 2 | 3 | 4 | 5 | 6 | 7 | 8 | 9 | 10 |
| Excellent | Very Good | Good | Fair | Poor | | | | | |

Enhancement Stability Index™

| | | | | | |
|------------------------|----------------------------|---------------|----------------------|------------------|--------------------------|
| None Extremely Rare | Insignificant Very Rare | Minor Rare | Moderate Uncommon | Strong Common | Prominent Very Common |
|------------------------|----------------------------|---------------|----------------------|------------------|--------------------------|

Degree of Clarity Enhancement & Relative Rarity™

Christopher P. Smith, President

